



AIRCOLOR PLASTIC PRIMER

H26

VERSION: 130325
Page:1/2

ADHESION PRIMER

DEFINITION

AIRCOLOR PLASTIC PRIMER is applied directly as a primer and has excellent adhesion on all plastic exterior and interior parts, including bumpers, mirrors and other plastic parts. Topcoat can be applied after approximately 10 minutes air dry at 20°C

AIRCOLOR PLASTIC PRIMER has a transversal nozzle allows the direction of application to be adjusted by the output nozzle (horizontal/vertical).

PHYSICAL CHARACTERISTICS

Nature:	Polyolefin resin	
Colour:	Transparent	
Specific weight:	0,8 kg/l at 20°C	
Propellant:	GLP	
Aerosol pressure:	4 bar at 20°C	
Dry film thickness:	1-2 microns	1 coat
Yield:	3-4 m ² / spray	
VOC:	<820 g/l	Application 2004/42/EC - IIB (e)(840)(<820)

SURFACE PREPARATION

PROCESS			Plastics (*)
	ROBRITE VF DA93		✓

(*) PP, PP/EPDM, ABS, SAN, PC, PA, PUR-RIM, R-TPU, PPO, PBT, PUR flexible foam, UP-GF plastics


APPLICATION

Transversal nozzle	2'	20-25 cm	1 coat	10'

REMARKS

Shake the aerosol before use for 2 minutes after hearing the steel mixing balls move. Carry out test spray.

EQUIPMENT CLEANING



*After use, turn
can upside
down and
spray for
several
seconds*

SAFETY

Follow instructions on the product label. For more information check the Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

GUARANTEE

In unopened original packaging, one year from manufacturing date.

For any technical information contact with our Customer Attention Service or our Technical Department. ROBERLO SA declines any responsibility due to an incorrect use of the product.